Łukasiewicz Research Network –
Poznań Institute of Technology
Ewarysta Estkowskiego 6, 61-755 Poznań

Centre of Laboratory Testing
Laboratory of Environmental Testing
Winiarska 1, 60-654 Poznań
• phone: +48 61 849 24 00 • e-mail: office.dbl@pit.lukasiewicz.gov.pl

Test report

no. DBL-2026-6418-01-BLS of 19.10.2026

AB 053

SUBJECT OF THE ORDER	Quality testing of wood pellets – SYLVA Sp. z o.o.
ORDER NUMBER	A/DBL/BLS/6418/2026
NAME AND ADDRESS OF ORDERING PARTY	**ORDERING PARTY** DQS Polska Sp. z o.o. ul. Domaniewska 45, 02-672 Warszawa
IDENTIFICATION OF TESTED OBJECTS	**TESTED OBJECT**

Name	Wood pellets
Producer	SYLVA Sp. z o.o. ul. Kościerska 2, 83-441 Wiele
ENplus® ID/ Sample No.	6mm/SYLVA/FD-2026-1

DATE OF ACCEPTANCE OF OBJECTS FOR TESTS	23.09.2026
PERFORMANCE DATE	02.10.2026
TESTING LOCATION	Laboratory headquarters
OPERATORS	Klaudia Sikorska, B.Eng.

	FULL NAME POSITION	**DATE, SIGNATURE**
Authorized by	Magdalena Czajka, PhD. Eng. Area Leader - Deputy Manager for Environmental Research	M. Czajka 19.10.2026

Test results relate only to the objects tested.
The test report may not be reproduced other than in its entirety without the written consent of the Laboratory Manager.

1. TEST METHODS

Name of the test	Document	Method status (A/NA)*
Total moisture	EN ISO 18134-2:2024	A
Fines content	EN ISO 5370:2023	A

*A – accredited method; NA – non-accredited method

2. EQUIPMENT OF THE TEST STANDS

Name	Type	Producer	ID No.
Laboratory balance	PS 6000/C/2	RADWAG	M3/50
Laboratory drier	RF115	BINDER	M1/48
Sieve 3.15 mm	-	RETSCH	M9/34

3. DESCRIPTION OF TEST SAMPLE

The object of the assessment was the sample of pellets with the diameter of 6 mm, described by the customer as pellets made of post-production chemically uncontaminated sawdust. Sample number: 6mm/SYLVA/FD-2026-1.

The sample was taken by the customer and delivered to the laboratory of Łukasiewicz Research Network - Poznań Institute of Technology on 23rd September 2026.

Identification number: A-6418/2026/1.

4. TEST RESULTS

Tests results are presented in Record No. 6418-01/2026.

5. ADDITIONAL INFORMATION

1. In the case of samples taken by the client, the Laboratory is not responsible for the identification and representativeness of the object, method and place of collection.
2. The expanded uncertainty was determined for coverage factor k = 2 and 95% confidence level. The measurement uncertainty does not take into account the uncertainty component associated with the sampling.

Record No. 6418-01/2026

Sample Name: Wood pellets
Name of Producer: SYLVA Sp. z o.o.
ul. Kościerska 2, 83-441 Wiele
ENplus® ID/ Sample No.: 6mm/SYLVA/FD-2026-1

Origin:		1. Woody biomass				
Traded form:		Wood pellets				
Classification of origin according to EN ISO 17225-1:2021		1.2.1 Chemically untreated by-products and residues from the wood processing industry				
Parameter	**Unit**	**Value**	**Uncertainty [±] [1]**	**Threshold values acc. to ENplus® ST 1001:2022**		
				A1	**A2**	**B**
Moisture	w-% $_{ar}$	6.3	0.3	≤ 10		
Fines (< 3.15 mm)	w-% $_{ar}$	0.17	0.02	≤ 1.0 (≤ 0.5%) [2]		

$_{d}$ dry $_{ar}$ as received
1. the expanded uncertainty was determined for coverage factor k = 2 and 95% confidence level
2. at factory gate, at the end of production or when loading truck for deliveries to end-users (< 0.5% when filling pellet bags or sealed big bags)

--- END OF REPORT ---